



Chapter	Subject	Spécifications		Tolérance
7	Chemical content	Monoammonium phosphate	30 %	28-32%
		Ammonium sulphate	44 %	42-46 %
		Heavy spar	25 %	23-27 %
5	Bulk density		0,91 g/ml	0,84-0,98g/ml
5	Sieve analysis (1)	Retained 125 um	20 %	15-25 %
		Retained 63 um	50 %	42-58 %
		Retained 40 um	60 %	52-68 %
10	Resistance to caking and lumping	Retained on seive 425 um	0 %	N.A. (2)
11	Water repellency	Water absorption	Absence	N.A. (2)
12	Moisture content		≤ 0,25 %	.A. (2)
(1) Method : method 2, annexe B (cumulative values)				
(2) N.A.: not applicable				